

BEST AVAILABLE COPY

PLI/GB 2004 / U 0 3 1 0 1



GB04/3101



INVESTOR IN PEOPLE

**PRIORITY
DOCUMENT**
SUBMITTED OR TRANSMITTED IN
COMPLIANCE WITH RULE 17.1(a) OR (b)

The Patent Office
Concept House
Cardiff Road
Newport
South Wales
NP10 8QQ

REC'D 27 AUG 2004

WIPO

PCT

I, the undersigned, being an officer duly authorised in accordance with Section 74(1) and (4) of the Deregulation & Contracting Out Act 1994, to sign and issue certificates on behalf of the Comptroller-General, hereby certify that annexed hereto is a true copy of the documents as originally filed in connection with the patent application identified therein.

In accordance with the Patents (Companies Re-registration) Rules 1982, if a company named in this certificate and any accompanying documents has re-registered under the Companies Act 1980 with the same name as that with which it was registered immediately before re-registration save for the substitution as, or inclusion as, the last part of the name of the words "public limited company" or their equivalents in Welsh, references to the name of the company in this certificate and any accompanying documents shall be treated as references to the name with which it is so re-registered.


In accordance with the rules, the words "public limited company" may be replaced by p.l.c., plc, P.L.C. or PLC.

Re-registration under the Companies Act does not constitute a new legal entity but merely subjects the company to certain additional company law rules.

Signed

Dated

Andrew Gersey
19 August 2004



Patents Form 1/77


Patents Act 1977
(Rule 16)



1/77

Request for grant of a patent

(See the notes on the back of this form. You can also get an explanatory leaflet from the Patent Office to help you fill in this form)



The Patent Office

Cardiff Road
Newport
South Wales
NP10 8QQ

1. Your reference

JOM/BK/267698.

2. Patent application number

(The Patent Office will fill in this part)

0317192.3

3. Full name, address and postcode of the or of each applicant (underline all surnames)

Smith & Nephew, plc
15 Adam Street
LONDON WC2N 6LA

Patents ADP number (if you know it)

03969284001

03969284006

If the applicant is a corporate body, give the country/state of its incorporation

4. Title of the invention

High Strength Bioresorbable Co-Polymers

5. Name of your agent (if you have one)

John Hobbs

"Address for service" in the United Kingdom to which all correspondence should be sent (including the postcode)

Smith & Nephew plc
Group Research Centre
York Science Park
Heslington
York YO10 5DF
United Kingdom

Patents ADP number (if you know it)

07260854001

6. If you are declaring priority from one or more earlier patent applications, give the country and the date of filing of the or of each of these earlier applications and (if you know it) the or each application number

Country

Priority application number
(if you know it)

Date of filing
(day / month / year)

7. If this application is divided or otherwise derived from an earlier UK application, give the number and the filing date of the earlier application

Number of earlier application

Date of filing
(day / month / year)

8. Is a statement of inventorship and of right to grant of a patent required in support of this request? (Answer 'Yes' if:

YES

- a) any applicant named in part 3 is not an inventor, or
 - b) there is an inventor who is not named as an applicant, or
 - c) any named applicant is a corporate body.
- See note (d))

Patents Form 1/77

9. Enter the number of sheets for any of the following items you are filing with this form.
Do not count copies of the same document

Continuation sheets of this form

Description

6

Claim(s)

Abstract

Drawing(s)

10. If you are also filing any of the following, state how many against each item.

Priority documents

Translations of priority documents

Statement of inventorship and right to grant of a patent (*Patents Form 7/77*)

Request for preliminary examination and search (*Patents Form 9/77*)

Request for substantive examination (*Patents Form 10/77*)

Any other documents
(*please specify*)

11.

I/We request the grant of a patent on the basis of this application.

Signature

Date 18/07/03

JOHN HOBBS

12. Name and daytime telephone number of person to contact in the United Kingdom

John Hobbs 01904 824050

Warning

After an application for a patent has been filed, the Comptroller of the Patent Office will consider whether publication or communication of the invention should be prohibited or restricted under Section 22 of the Patents Act 1977. You will be informed if it is necessary to prohibit or restrict your invention in this way. Furthermore, if you live in the United Kingdom, Section 23 of the Patents Act 1977 stops you from applying for a patent abroad without first getting written permission from the Patent Office unless an application has been filed at least 6 weeks beforehand in the United Kingdom for a patent for the same invention and either no direction prohibiting publication or communication has been given, or any such direction has been revoked.

Notes

- If you need help to fill in this form or you have any questions, please contact the Patent Office on 08459 500505.*
- Write your answers in capital letters using black ink or you may type them.*
- If there is not enough space for all the relevant details on any part of this form, please continue on a separate sheet of paper and write "see continuation sheet" in the relevant part(s). Any continuation sheet should be attached to this form.*
- If you have answered 'Yes' Patents Form 7/77 will need to be filed.*
- Once you have filled in the form you must remember to sign and date it.*
- For details of the fee and ways to pay please contact the Patent Office.*

HIGH STRENGTH BIORESORBABLE CO-POLYMERS

The present invention relates to polymer compositions and artefacts made therefrom. In particular the present invention relates to polymers having high mechanical strength and their use for the manufacture of load bearing medical devices suitable for implantation within the body. More particularly the invention relates to bioresorbable glycolic acid-containing co-polymers and to implantable medical devices made therefrom.

Polymer compositions comprising poly-glycolic acid (PGA) and glycolic acid-containing co-polymers have an established use for medical implants. It has also been proposed that certain mechanical properties may be improved by extruding PGA melts or by drawing PGA in a plastic state. Isotropic PGA has a tensile strength of between 50 to 100 MPa and a tensile modulus of between 2 and 4 GPa. A commercial product (SR-PGA) comprising PGA fibres in a PGA matrix has a flex strength and modulus of 200 – 250 MPa and 12 – 15 GPa, respectively. It is also reported in the literature that melt spun PGAs have tensile strength of about 750 MPa and a modulus from 15 to 20 GPa. In US Patent No. 4968317 an example of a drawn PGA is stated to have a tensile strength of about 600MPa.

Although PGAs having improved strength characteristics are known, none of the known materials have the mechanical properties approaching those of the metals conventionally used for load bearing implantable medical devices. A commercial alloy used for orthopaedic implant devices, known as Ti-6-4, comprises titanium with 6% aluminium and 4% vanadium and has a tensile strength in the range of 800 to 1000MPa and a modulus in the order of 100GPa.

One possible reason that PGA and glycolic acid-containing co-polymers cannot currently be processed to achieve the desired strength of metals is that when the polymers are processed by common methods to produce orientated fibres (e.g. stretching the material at a constant rate in a heated chamber or

tank) additional polymer crystallisation occurs during the process. The crystals in the polymer act such that they prevent further polymer orientation. This crystallisation of the polymer limits the mechanical properties that can be achieved by drawing glycolic acid-containing co-polymers to around 800MPa, as described in the prior art.

We have found that polymer compositions comprising glycolic acid-based co-polymers may be processed such that the resultant composition has significantly greater strength, typically of the order of greater than 1200MPa with a commensurate increase in modulus, typically in excess of 22 GPa.

10 In accordance with the present invention there is provided a polymer composition comprising glycolic acid as a co-polymer with at least one other bioresorbable monomer, or a functional derivative of said co-polymer, having a tensile strength of at least 1200MPa.

15 The polymer composition gains this level of tensile strength by means of a novel processing method that results in an orientated structure, for example an orientated fibre.

The present invention further provides an artefact comprising a polymer composition including glycolic acid or a functional derivative thereof having a tensile strength of at least 1200MPa.

~~20 The polymer composition may be comprised entirely of glycolic acid-based co-~~
 polymer or a derivative thereof, or may comprise a glycolic acid-based co-polymer-containing blend with other polymers. Preferably the polymer composition is entirely glycolic acid-based co-polymer.

25 Similarly, artefacts formed from the polymer compositions of the invention may consist wholly of the polymer compositions of the invention or may be composites consisting only partially of the polymer compositions of the invention.

Aptly the artefact contains 10 to 80% by volume of the polymer compositions of the invention, suitably the artefact contains up to 60% by volume of the

polymer compositions of the invention, preferably the artefact contains at least 40% by volume of the polymer compositions of the invention and typically the artefact contains approximately 50% by volume of the polymer compositions of the invention.

- 5 We have found that in order to achieve the high strength exhibited by the compositions of the invention it is necessary that the glycolic acid-containing co-polymer be rendered into an amorphous state and then immediately drawn to form a highly orientated structure.

10 This can be achieved by first processing isotropic glycolic acid-based co-polymer granules to form fibres or filaments, thereafter passing the fibres into a quenching bath to form an amorphous structure. Polymer compositions of the present invention may then be produced by drawing the quenched, amorphous glycolic acid-based co-polymer. Preferably this is a drawing process which minimises the time polymer is exposed to elevated
15 temperatures, thus minimising the time for the polymer to crystallise.

In accordance with another aspect of the invention there is provided a process for the manufacture of glycolic acid-based co-polymer compositions comprising increasing polymer chain orientation of a substantially amorphous polymer by drawing at localized points within the mass.

- 20 Suitably this comprises the steps of forming glycolic acid-based co-polymer or a functional derivative thereof into fibres, for example by melt extrusion or solution spinning; quenching the fibres then subjecting the quenched fibres to a tension under conditions whereby a defined region of the tensioned fibres is drawn.
- 25 Aptly fibres of amorphous glycolic acid-based co-polymer-containing polymers may be prepared by solution spinning or melt extruding the polymer through a die; the filament is then rapidly chilled to produce a substantially amorphous material. Typical chilling methods include blowing a cold gas onto the filament
-

as it is produced or by passing the filament through a bath of a suitable cold liquid, e.g. water, silicone oil.

A suitable drawing method is zone heating. In this process a localised heater is moved along a length of fibre which is held under constant tension. This process is used in the zone-drawing process as described by Fakirov in Oriented Polymer Materials, S Fakirov, published by Hüthig & Wepf Verlag, Hüthig GmbH. In order to carry out this zone heating fibre can be passed through a brass cylinder. A small part of the cylinder inner wall is closer to the fibre, this small region locally heats the fibre, compared to the rest of the brass cylinder, localising the drawing of the fibre to this location, see figure 1. A band heater can be placed around the brass cylinder to allow it to be heated above room temperature. This heated brass cylinder can then be attached to the moving cross-head of a tensile testing machine and the fibre to be drawn suspended from a beam attached to the top of the testing machine. To draw the fibre a weight can be attached to the lower end of the fibre, the brass cylinder heated to the desired temperature and the cross-head moved to the lower end of the fibre, see figure 2. The polymer draws where the fibre is closest to the brass cylinder, as the cross-head is moved up the length of the fibre, then a length of the fibre can be drawn.

Suitably the fibre can be held taut using a small stress, which is typically below the yield point of the material at ambient temperatures. The fibre can then be heated locally to a temperature which is above the softening point

(T_g) but below the melting point such that localised drawing of the polymer occurs, the whole fibre can be treated by movement of either or both the fibre and heated zone such that the full length of the fibre is drawn. This first drawing of the polymer may produce a polymer with improved molecular alignment and therefore strength and modulus. In this first step the conditions are selected such that the material does not substantially crystallise during the process, this requires that either the temperature of the polymer is below the temperature at which crystallisation occurs, T_c , or if the polymer is above T_c the speed at which the heated zone moves along the fibres is fast enough such that the polymer cools below T_c before it has time to crystallise. Further

improvements can be made by subsequent treatments, where the stress applied to the fibre or the zone temperature is increased or both. Both the strength of the fibre and the softening point increase as the degree of molecular alignment improves. The process can be repeated many times, until
5 the desired properties are reached. A final annealing step can be carried out in which the material crystallises under tension in the process; this can further improve the mechanical properties and improve the thermal stability of the final fibre.

In an embodiment of this aspect of the invention there is provided an artefact
10 comprising a poly-glycolic acid in accordance with the invention. For example, the glycolic acid-containing co-polymer fibres can be mixed with other components to form the artefacts. These other components may be polymers, bioresorbable polymers, non-polymeric materials or combinations thereof.

15 Aptly the bioresorbable polymer comprises a poly-hydroxy acid, a poly-caprolactone, a polyacetal, a poly-anhydride or mixture thereof; the polymer comprises poly-propylene, poly-ethylene, poly-methyl methacrylate, epoxy resin or mixtures thereof whilst the non-polymeric component comprises a ceramic, hydroxyapatite, tricalcium phosphate, a bioactive factor or
20 combinations thereof.

Suitably the bioactive factor comprises a natural or engineered protein, a ribonucleic acid, a deoxyribonucleic acid, a growth factor, a cytokine, an angiogenic factor or an antibody.

Artefacts according to the present invention can aptly be manufactured by
25 placing appropriate lengths of strengthened glycolic acid-containing co-polymer fibre into moulds, adding the other components then compression moulding. Alternatively, the strengthened fibres can be pre-mixed with the other components then compression moulded.

In an alternative processing method, artefacts according to the present
30 invention can be manufactured by forming a polymeric component in the

presence of the strengthened fibres by in situ curing of monomers or other precursors for said polymeric component.

Preferably the monomers used in this process do not liberate any by-products on polymerisation as these can compromise the properties of the artefact.

- 5 Aptly at least one of the monomers used in said in situ curing process is a ring-opening monomer that opens to form a poly-hydroxy acid. Typically at least one monomer is a lactide, a glycolide, a caprolactone, a carbonate or a mixture thereof.

10 The polymer compositions of the invention are useful for the production of medical devices, particularly implantable devices where it is desirable or necessary that the implant is resorbed by the body. Thus, artefacts in accordance with the present invention include sutures; tissue-engineering scaffolds or scaffolds for implantation; orthopaedic implants; reinforcing agents for long fibre composites used in resorbable load bearing orthopaedic
15 implants; complex shaped devices, for example formed by injection moulding or extruding composites formed by mixing short lengths of chopped fibres with poly-lactic acid; or bone fixation devices, for example formed from relatively large diameter rods (e.g., greater than 1mm) of the compositions of the invention.

20 ~~The invention will now be illustrated by the following example.~~

Example 1

PGA:PLA co-polymer (98% PGA, 2% PLA) was extruded into a water bath to produce a translucent fibre of approx 0.5mm diameter. This fibre was then
25 suspended vertically and a weight of 200g was applied. A heated cylinder of brass with a hole of approx 15mm apart from a small section with a 2mm diameter hole, through which the PGA fibre passes, was heated to a temperature of 90°C and moved along the fibre at a speed of 200 mm/min. The fibre produced was found to have a strength of greater than 1200 MPa
30 and a modulus of greater than 20 GPa.

**This Page is Inserted by IFW Indexing and Scanning
Operations and is not part of the Official Record**

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☐ **BLACK BORDERS**
- ☐ **IMAGE CUT OFF AT TOP, BOTTOM OR SIDES**
- ☒ **FADED TEXT OR DRAWING**
- ☐ **BLURRED OR ILLEGIBLE TEXT OR DRAWING**
- ☐ **SKEWED/SLANTED IMAGES**
- ☐ **COLOR OR BLACK AND WHITE PHOTOGRAPHS**
- ☐ **GRAY SCALE DOCUMENTS**
- ☒ **LINES OR MARKS ON ORIGINAL DOCUMENT**
- ☐ **REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY**
- ☐ **OTHER:** _____

IMAGES ARE BEST AVAILABLE COPY.

As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.